

### Firestop 3000 Fire-retardant silicone elastomer

A component silicon based glue for fireseal systems.

**Density:** 1400 kg/m<sup>3</sup>

**Application Temperature:** 5-35°C

**Working Temperature:** -65°C to 250°C

**Curing Time (15mm thk):** ca. 2 weeks

**Working Time:** 20 - 30 minutes

**Elongation:** 1300 %

**Hardness Shore A:** 15 points

**Tensile Strength:** 0.7 MPa

**Halogen Content:** < 2 ppm

**Electrical Property:** Insulating

**Shelf Life:** 12 months



Part Number	Description	Colour
102665	FIRESTOP SEALANT 3000,310ml cartridge	white
102676	FIRESTOP SEALANT 3000,310ml cartridge	grey
102687	FIRESTOP SEALANT 3000,310ml cartridge	black

### D24-B Fire-retardant silicone elastomer

A component silicon based glue for fireseal systems.

**Colour:** Off-white

**Density:** 96 kg/m<sup>3</sup>

**Halogen Content:** < 2 ppm

**Working Temperature:** 1200°C



Part Number	Description	Package (strips/pack)
102698	Blanket D-24B,Calcium Silicate Fibre,7300x600x25 mm	1
102709	Blanket D-24B,Calcium Silicate Fibre,7300x100x25 mm	6
102720	Blanket D-24B,Calcium Silicate Fibre,7300x100x25 mm	1